

VALORI ISOLAMENTO TERMICO PANNELLI POLIURETANO CALCOLATI SECONDO NUOVA NORMATIVA EN 14509 A.10 (MARCATURA CE)

TERMOPARETI®

BUBBLE • RUGBY • WP/ST • WPM/C-FN • WPM/C • TPG/C-ST • TPM/C-ST
TPL/C-ST • TPG/C-LAB

U	SPESSORE mm									
	25	35	40	50	60	80	100	120	150	180
Kcal/h m ² °C	0,711	0,522	0,461	0,372	0,313	0,237	0,191	0,160	0,129	0,108
W/m ² °K	0,827	0,607	0,536	0,433	0,364	0,276	0,222	0,186	0,150	0,125

TERMOCOPERTURE®

TCP/C • RP/ST 4G • RP/ST 3G • TCP/C RAME • HELIOS

U	SPESSORE mm					
	30	40	50	60	80	100
Kcal/h m ² °C	0,602	0,461	0,372	0,313	0,237	0,191
W/m ² °K	0,700	0,536	0,433	0,364	0,276	0,222

TERMOCOPERTURE FLEX®

RP/ST FLEX-AC/CB* • RP/ST FLEX-DECK* • ZOOTECH* • POLIOLEFINE*

U	SPESSORE mm					
	30	40	50	60	80	100
Kcal/h m ² °C	0,602	0,461	0,372	0,313	0,237	0,191
W/m ² °K	0,700	0,536	0,433	0,364	0,276	0,222

* Pannelli senza marchio CE perchè non previsto dalla norma

SERBOND®

WP/ST FLAT • WP/ST BUBBLE • WP/ST RUGBY
WPM/C-FN FLAT • WPM/C-FN BUBBLE • WPM/C-FN RUGBY

U	SPESSORE mm			
	40	50	60	80
Kcal/h m ² °C	0,461	0,372	0,313	0,237
W/m ² °K	0,536	0,433	0,364	0,276